

Material

20 F 55102

revision index

1

revision date

10/19/2009

page

1 / 2

Physical properties

Density

DIN EN ISO 1183-1, 23 °C

required

2.22 ±0.04

actual

2.23

g/cm³

Hardness

DIN ISO 7619-1, Shore D, 23 °C

63 ±2

62

Shore

Tensile strength

DIN 53455, S2, 23 °C

> 14

17.5

MPa

Elongation at Break

DIN 53455, S2, 23 °C

> 180

225

%

Material 20 F 55102

revision index

1

revision date

10/19/2009

page

2 / 2

No ASTM D2000 properties available

Temperature-range: - 150 °C to 260 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.