

Material

55 SBR 635

revision index

1

revision date

9/15/2005

page

1 / 2

Physical properties

Density

DIN EN ISO 1183-1

required

actual

1.32

g/cm³

Hardness

DIN ISO 7619-1

55

Shore

Rebound resilience

DIN 53512

40

%

Modulus

100 %, DIN 53504, S2

2

MPa

Tensile strength

DIN 53504, S2

7.6

MPa

Elongation at break

DIN 53504, S2

500

%

Material **55 SBR 635**

revision index

1

revision date

9/15/2005

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.