

Material

92 AU 21100

revision index
6

revision date
2/7/2011

page 1 / 2

Physical properties

	required	actual	
Density DIN EN ISO 1183-1, 23 °C	1.13 ±0.02	1.13	g/cm³
Hardness DIN ISO 7619-1, Shore A, 23 °C	92 ±5	92	Shore
Tensile strength DIN 53504, S2, 23 °C	> 40	58	MPa
Elongation at break DIN 53504, S2, 23 °C	> 500	630	%
Modulus 50 %, DIN 53504, S2, 23 °C	> 8	9	MPa
Tear strength DIN 53507, A, 23 °C	---	96	KN/m
Compression set DIN ISO 815, B, 24 h, 70 °C, 10 %	---	26	%
Compression set DIN ISO 815, B, 24 h, 100 °C, 20 %	---	35	%
Compression set DIN ISO 815, B, 70 h, 100 °C, 10 %	---	44	%
Low Temperature DIN 53765, DSC	---	-54	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-42	°C

Material 92 AU 21100

revision index

6

revision date

2/7/2011

page

2 / 2

No ASTM D2000 properties available

Temperature-range: -50 °C to 110 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.