



DICHTOMATIK
Any seal. Any time.

a brand of
FREUDENBERG

Technical data sheet in accordance with ASTM

Material FKM FP802701

black

cross linking: bisphenolically

print date	revision index	revision date	page	1/1
10/2/2017	2	7/3/2017		
Physical properties		required	actual	
Density ASTM D297		1.91 ±0.03	1.91	g/cm ³
Hardness ASTM D 2240, Shore A		80 ±5	80	Shore
Tensile strength ASTM D412		---	14.3	MPa
Elongation at Break ASTM D412		---	175	%
Tear strength ASTM D 624, B		---	31	KN/m
Low-temperature resistance ASTM D 746		---	-17	°C
Low temperature test ASTM D1329, TR10		---	-17	°C
Compression set ASTM D395, B, 70 h, 200 °C, 25 %		---	20	%
Temperature range		-20°C to 200°C		
Certificates	Country	Part	Remark	Expires unlimited
DVGW Baumusterprüfzertifikat Gas RoHS	D		DIN EN 549 H3 E1 2015/863/EU and 2011/65/EU	01 / 2022 ☐ ☒

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
Material Center Hamburg
Viviane Rellstab

Phone: +49 40 66989 316
Fax: 040 66989 9316
Email: Viviane.Rellstab@dichtomatik.de